power-xtra

Model Power-Xtra PX15SCFT - 1.2V 1500 Mah - SC - Ni-Cd Battery - Flat - 3C

Stock Code 900.600.503.375

| Item | Specifications | Conditions | |
|---|-----------------------------|---|--|
| Nominal Voltage | 1.2V | | |
| Nominal Capacity | 1.580 mAh | Standard Charge/Discharge | |
| Minimum Capacity | 1.500 mAh | | |
| Standard Charge | 150 mA (0.1C) × 16 hrs | Ambient temperature of 20±5°C, Relative Humidity: 65±20% | |
| Standard Discharge | 300 mA (0.2C) | to 1.0V/cell / -20°C to 60°C | |
| Fast Charge | 1500mA for 1.3 hours | -delta V controlled: 15mV/cell cut-off dT/dt controlled: 1°C per min | |
| Trickle Charge | 45 mA to 75 mA. | Ta=0~45°C | |
| Fast Discharge | 1.500mA to 1.0V | 10°C to 40°C | |
| Maximum Continuous Discharge Current | 4.500 mA | 3.0C | |
| Storage Temperature | -20 ℃ ~ 35℃ | Discharged state | |
| Weight | 47gr. / approx. | | |
| Open Circuit Voltage(OCV) | ≥1.25V | Within 1hr after standard charge | |
| Internal Impedance | ≤25mΩ | The initial internal resistance is measured at 1KHz within 1-4 hours after standard charge. | |
| Overcharge | No leakage nor explosion | The overcharge test is measured with a discharge current of 0.2C and a discharge final voltage of 1.0V/cell within 1-4 hours after charging for 28 days at a current of 0.1C. Check cell appearance after overcharge. | |
| Charge Retention | ≥300mA | After standard charge and storage time of 28 days at an ambient temperature of 20°C±2°C, the capacity is measured with a discharging current of 0.2C and a discharge final voltage of 1.0V. | |
| Cycles Test | ≥500 Cycle | IEC61951-2:2003 | |


power-xtra

Model Power-Xtra PX15SCFT - 1.2V 1500 Mah - SC - Ni-Cd Battery - Flat - 3C

Stock Code 900.600.503.375

| Item | Specifications |
|----------|-------------------|
| Diameter | 23.0 +0 / -1.0 mm |
| Height | 43.0 +0 / -1.5 mm |
| High Top | - |

Drawings



Image

